

AD-550

Quick Finish Clear



Technical Data

Color:	Clear
Mix Ratio:	4:1
Activator:	AD-551,552,553
Weight Solids(RTS):	29%
Film Build:	0.8-1.0 mils
Coverage:	465 sq ft./gal
Dry Time:	20 Minutes
Pot Life:	4-5 hours with #551, 8-10 hours when using #552 or #553
V.O.C.	4.4 lbs/gal

AD-550 is a 4.4 VOC medium solids urethane clearcoat designed for overall & panel refinishing. It is a fast drying user friendly clearcoat that produces an extremely durable finish. Excellent use in air and force dry environments.

Features:

- Easy Application
- Fast Dry
- Air Dry or Bake

Advantages:

- Less Buffing
- Same Day Delivery
- Versatile

Benefits:

- Increase Productivity
 - Reduces Delivery Time
 - Fits Most Shop Conditions
-

Special Instructions

1. Apply 2-3 wet coats, allowing a 10-15 minute flash time.
 2. Allow to dry 8-12 hours when using #551 Activator, 14-16 hours when using #552 Activator and Overnight when using #553 Activator at 77°F or 30 minutes at 140°F with a 1 hour cool down before sanding or polishing
-

Compare To:

Morton®	2750
Dupont®	V7500S
BASF®	DC-76