

AD-304, 312 2K Primer/Surfacer



Technical Data

Color:	Buff, Gray
Mix Ratio:	4:1
Activator:	AD-305
Weight Solids(RTS):	38%
Film Build:	1.0-1.5 mils
Coverage:	609 sq ft./gal
Dry Time:	2-4 Hours
Pot Life:	1 ½ - 2 Hours
V.O.C.	4.6 lbs/gal

AD-304 is a quality two component acrylic urethane primer surfacer formulated as a high build sanding primer surfacer, or a non sanding urethane sealer. #304 2-K urethane primer exhibits excellent fill, fast dry, sands easily, and provides excellent color holdout because it does not shrink.

Features:

- High Solids
- User Friendly
- Maximum Holdout

Advantages:

- Fills Quickly
- Easy Sanding
- Shrink Resistant

Benefits:

- Increased Productivity
 - Labor Savings
 - Best Final Results
-

Special Instructions

1. For maximum adhesion and corrosion resistance, treat bare metal with a quality metal conditioning system
 2. Apply 2-3 wet coats with a 10-20 minute flash time
 3. Allow to dry 1.5-3 hours at 77°F or 20 minutes at 140°F before sanding
-

Compare To:

PPG®	K-36, K-200, NCP-280 Acrylic Urethane Primer Surfacer
Dupont®	1140S, 3240S Uro® Primer-Filler
Sherwin Williams®	E2A-820, 210P22
BASF®	DP-20, 21
Transtar®	6921, 6504
Montana®	PS-5006A