



Spot refinishing
Plastic Bumper
Metal Fender

[View Label \(English/Español\)](#)

[View MSDS](#)

Adhesion Promoter

Bulldog Adhesion Promoter is designed to promote paint adhesion to all automotive surfaces, even profl works equally well on all flexible or rigid plastics, fiberglass, aluminum, glass, chrome, vinyl, galvanized painted surfaces. Bulldog acts as a tie coat by allowing several different surfaces to be painted at the same time to assure a smooth, flawless, durable finish every time. If added to the paint, it will perform as a flex agent, providing flexibility on plastics.

Product Number / Size

QTPO123 - Quart
GTPO123 - Gallon

Directions for use ▼

DIRECTIONS FOR USE:

Carefully read all cautions and instructions before use. Protect hands with solvent resistant gloves and eye glasses. Shake thoroughly and filter before each use to secure uniform mixture. Looks hazy, dries clear.

New flexible and rigid bumpers and other plastic exterior/interior parts: Clean thoroughly with Bulldog Bumper Cleaner. Rinse completely with water and let the part dry. Apply 2 to 3 coats of Bulldog Bond•F•T allowing it to flash 2 to 3 minutes between coats. Apply finish color coat wet on wet.

Edging and ground effects repainting: For edging new parts, no sanding is required. Clean the area to be painted with Auto Prep and blow off the excess solvent and dust. Apply 2 medium coats of Bulldog B•F•T Coat wet on wet, flash 2 to 3 minutes and spray color coat.

For ground effects, remove dust and grease with Bulldog Abrasive Bumper Cleaner. Rinse thoroughly with water and let the part dry. Apply 2 medium coats of Bulldog B•F•T Coat wet on wet, let it flash 2 to 3 minutes and spray finish color coat.

Spot and panel repair: After application of primer to all bare metal and body filler areas, sand all areas with 320 grit or finer sandpaper. Apply 2 medium coats of Bulldog B•F•T Coat allowing it to flash 2 to 3 minutes and before applying color. To add flexibility to the color and clear coat, follow directions from the a

Sanding Bulldog Bond•Flex•Tie Coat: Normally Bulldog B•F•T Coat should not require sanding, but should arise, allow 30 to 60 minutes drying time before wet sanding with 400 grit or finer sandpaper.

Cleanup: All tools and spills should be cleaned immediately with lacquer thinner. Care should be taken to remove thinner away from freshly finished surfaces.

NOTE: To ensure compatibility of Bulldog with enamel paints, mix a small amount of Bulldog with the paint to cure or clabbers. If this occurs, Bulldog should not be mixed with this paint system. However, it can serve as an adhesion promoter and sealer if sufficient time (approx. 30 minutes) is allowed to flash off before applying enamel base coat.

Related Items ▶

[Flexible Bumper Paint Stripper](#)

Flexible Bumper Paint Stripper

[Adhesion Promoter Aerosol](#)

Promotes paint adhesion

© Copyright 2007 W.M. Barr & Co., Memphis TN | P.O. Box 1879 Memphis, TN 38103 | 1-800-238-2672