

## MIR Compliant HIGH #5 – Beige, Gray, Dark Gray & White

Ready to Use High Build Primer

| Description                                  | <ul> <li>HIGH #5 is a ready to use high build primer/filler in an aerosol. It is used for priming uneven surfaces before top coating.</li> <li>High #5 is capable of producing a coating of a film thickness similar to that of a spray gun applied primer. The convenience of using a high build primer in an aerosol means that masking is kept to a minimum. Mixing paint and cleaning spray equipment are avoided as a result of using HIGH #5 leading to savings in time and materials.</li> <li>HIGH #5 is cromate free and easy to sand.</li> </ul>             |
|--|--|
| Surface preparation and instructions for use | <ul> <li>HIGH #5 can be applied to the following surfaces:-</li> <li>Fully cured paint.</li> <li>Polyester bodyfillers and F.R.P.</li> </ul>   |
|  | Thoroughly clean and degrease surfaces with a suitable panel wipe or thinner. Abrade wet or dry with 280-320 grit abrasive, re-clean, dry and degrease.  |
| Health and Safety Statement                  | FOR PROFESSIONAL USE ONLY. Read full instructions before use.<br>IMPORTANT: This product contains hazardous materials and therefore<br>appropriate personal protective equipment should always be used.<br>Please refer to the label and consult the material safety data sheet for<br>full handling instructions and personal protection information. These<br>are available via your local stockist or via the U-POL website at<br><u>WWW.U-POL.COM</u> . U-POL disclaim any liability where the user<br>does not wear the recommended personal protective equipment |
| Application                                  | Shake can thoroughly before use for a minimum of<br>2 minutes.<br>Apply 1-2 light even coats.<br>Allow 5-10 minutes flash off time between coats.  |
| Drying time                                  | Allow 10-20 minutes before overcoating.<br>Drying time is dependent upon film thickness, humidity and temperature.   |
| Over-painting                                | <b>HIGH #5</b> should be flatted wet with 600-800 grit or dry with 400-600 grit abrasive. <b>HIGH #5</b> may be over-painted with most paint systems.  |
| VOC Information                              | MIR Ref. ABP:MIR1.55   |
| Product code                                 | ALL Aerosols are 450 mls.<br>UP0783 – (Beige)<br>UP0791 - (Gray)<br>UP0763 - (White)<br>UP0765 – (Dark Gray)<br>UP0783V - (Beige) 2.1 VOC Compliant<br>UP0791V - (Gray) 2.1 VOC Compliant<br>UP0765V – (Dark Gray) 2.1 VOC Compliant<br>UP0763 – (White) 2.1 VOC Compliant   |

USA U-POL Representative - Sanders and Associates Inc. 1263 Route 31 South, Lebanon, NJ 08833 Tel: (908) 730 8858 or (800) 340 7824 Fax: (908) 730 6621 or (800) 787 5150 E-mail <u>upol@earthlink.net</u> Website : <u>WWW.U-POL.COM</u>