

2 - 6101 Klearkote

1 - 6102, 6103, 6104 Activator

#6101 FEATURES

1

• 4.2 VOC

2

- 2:1 Mix Ratio
- Easy to Apply in 2 3 Coats
- Excellent Flowout
- Great Gloss & Distinctness of Image
- Superior Durability
- 3 Activators to Choose From

XTREME EuroStar 4.2 VOC Klearkote

#6101-5 5 Liter

XTREME EuroStar 4.2 VOC Activators

#6102-2.5 Fast - 2.5 Liter #6103-2.5 Medium - 2.5 Liter #6104-2.5 Slow - 2.5 Liter



REME Just Shoot It!

EUROSTAR

4.2 VOC EuroStar KlearKote



Taking Bodyshop Productivity to the XTREME!

6101 XTREME EuroStar is a European medium solids klearkote that is easy to spray offering excellent flowout, gloss, and durability. With three activators to choose from, XTREME EuroStar provides versatility in most shop conditions. 6101 can be used for partial or complete paint jobs in need of a high gloss, durable finish.

Call 1-87REFINISH (1-877-334-6474) to find your local 5 Star Autobody Products supplier. Or visit our website: www.autobodybrands.com

©2007 ABI/ A division of I.A.M.G. Autobody Brands International Part # 6101,6102,6103, 6104 Printed 12/07





6101

4.2 VOC EuroStar Klearkote

PRODUCT DESCRIPTION:

6101 EuroStar klearkote - An advanced new Klearkote system designed to maximize speed and ease-of-use in the collision repair

shop. Formulated using advanced European technology, 6101 is a tough, durable urethane that helps make shops more productive. Because it provides great gloss direct from the gun, buffing is minimized. Provides high build, dries fast and is easy to spray with excellent flow out and leveling. Use on a variety jobs - from small repairs to overall refinishing.

PRODUCTS:

XTREME EuroStar 4.2 VOC Klearkote

#6101-5 5 Liter

XTREME EuroStar 4.2 VOC Activators

#6102-2.5 Fast - 2.5 Liter #6103-2.5 Medium - 2.5 Liter Slow - 2.5 Liter

#6104-2.5

Mask vehicle to protect from overspray. Apply basecoat and allow to dry according to paint

MIXING DIRECTIONS:

manufacturer's directions.

SURFACE PREPARATION:

Combine components by volume. Mix thoroughly and strain before using.

• 2 Parts #6101EuroStar Klearkote – 4.2 VOC

• 1 Part #6102, 6103, or 6104 Activator



APPLICATION DIRECTIONS:

Number of Coats: Wet 2 coats

Application Density: Medium wet to wet

Overlap: 50%

FLASH TIME: 5 – 10 minutes in between

coats (@ 72° F / 22° C)

Film Thickness Range: 2-4

Application Conditions:

Minimum Temp: 50°F (Substrate Temp.) Max Temp: 100°F (Substrate Temp.)

Ambient Humidity: Less than 80% preferred

TIME TO BUFF: 18 - 24 hours (@ 72° F / 22° C). Excessive film build and cool temperatures will

extend dry times.

ADDITIVES:

ACCELERATOR: N/A

FISHEYE: N/A FLEX ADDITIVE: Not required

6104 @ or

Note: Do not spray when surface temperature is below 50°F. Commercially available basecoats with a VOC less than 6.6 lbs/gal

6103 @ or

Properly prepared previously painted substrates.

GUN SETUPS:

SUBSTRATES:

CONVENTIONAL

POT LIFE:

1 – 2 Hours @ 72°F / 22°C

CLEAN UP:

Clean spray equipment immediately after use with gun wash solvent.

AIR PRESSURES Conventional @ Gun **HVLP** @ **Cap**8-10 psi

FLASH/DRY TIMES:

above 72°F above 85°F above 95°F Flash Between Coats 5-10 min 5-10 min 5-10 min **Dust Free** 10-15 min 10-15 min 10-15 min Sand/Polish 18-24 hours 18-24 hours 18-24 hours

6102 @ or

Force Dry (Convection Heat)

Purge time before applying heat 0-15 min 0-15 min 0-15 min Force Dry Time 20 min @ 165°F 20 min@ 165°F 20 min@ 165°F Sand and Buff After Cool Down After Cool Down After Cool Down

TECHNICAL DATA:

(Ready To Spray)

Flash Point: 5–10 minutes in between coats (@ 72° F / 22° C) Weight Solids: 43.59%

Film Build: Cool temperatures will extend dry times Theoretical Coverage: 2.9 sq. ft per 100 ml @ 3 mils

VOC (Volatile Organic Content): 4.2 lbs/gal

Viscosity: Seconds Zahn #2

SAFETY INFORMATION - FOR INDUSTRY USE ONLY

Danger: Vapor and spray mist harmful. Overspray may cause lung damage. May cause allergic skin and respiratory reaction, effects may be permanent. Flammable liquid and vapor. Harmful if inhaled. May affect the brain or nervous system causing dizziness, headache, or nausea. May cause eye, skin, nose, and throat irritation. Contents: See product label for contents and CAS #'s. The contents of this package must be blended with other components before the product can be used. Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions. The material id designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public. KEEP OUT OF REACH OF CHILDREN

