



## UP2282

### SERIES S2028 HIGH BUILD LACQUER PRIMER

Description	<p><b>UP2282</b> is a fast drying, high build lacquer primer. It is designed to fill surface scratched or similarly defective metal, stone chip damage, polyester body filler, glass fibre mouldings and most factory or refinish paint systems except air dried synthetics. <b>UP2282</b> is supplied ready for use. It will <b>sand</b> easily to a feathered finish and can be used as a primer under lacquer, 2 pack acrylic and synthetic top coats.</p>
Surface preparation and instructions for use	<p><b>UP2282</b> can be applied to the following surfaces:-</p> <ul style="list-style-type: none"><li>• Bare metal such as steel and aluminium (etch primers are recommended over aluminium).</li><li>• Polyester fillers.</li><li>• Original paint surfaces (with the exception of thermoplastic acrylics).</li></ul> <p>Thoroughly clean and degrease surfaces with a suitable spirit wipe or thinner. Abrade with P180 paper for bare metal or 240 paper for painted surfaces. AFTER PREPARATION CLEAN THOROUGHLY - DRY THOROUGHLY.</p>
Health and Safety Statement	<p>FOR PROFESSIONAL USE ONLY. Read full instructions before use. IMPORTANT: This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at <a href="http://WWW.U-POL.COM">WWW.U-POL.COM</a>. U-POL disclaim any liability where the user does not wear the recommended personal protective equipment</p>
Application	<p>Stir well before use. Minimum recommended working temperature is 55°F with a gravity fed or a suction gun. Use a 1.6mm-2.0mm fluid tip. Hold gun 15-20 cm's from panel. Apply 2-3 coats as required, allowing 5-10 minutes between each coat.</p>
Thinners	<p><b>UP2282</b> is supplied ready for use. However, up to 50% of top grade lacquer thinner may be added if necessary. Use standard gun wash or lacquer thinner to clean gun.</p>
Build and pressure	<p>One even coat of <b>UP2282</b> will give a build of approximately 20-40 microns.</p>
Drying time	<p>1 hour at 72°F or 20 mins. at 140°F. Drying time is dependent upon film thickness, humidity and temperature.</p>
Over-painting	<p>Wet or dry <b>sand</b>, clean and dry thoroughly, <b>UP2282</b> may then be over-painted with most paint systems. <b>UP2282</b> should be overcoated within 6 hours of application.</p>
Product code	<p><b>UP2282</b> - 1 gallon tin - gray</p>