

# U-POL PRODUCTS HS GRAVITEX PLUS

## Stone Chip Protector

### Description

**GRAVITEX PLUS** is a tough, hard, durable coating designed to reproduce the manufacturers original stone chip finish. It will protect against stone chips, salt, damp and rust. **GRAVITEX PLUS** will also help to deaden sound and vibrations and is, therefore, ideal for application to panels and inside engine compartments. The high build formula will cover weld marks and seams, often in one application.

### Surface preparation and instructions for use

**GRAVITEX PLUS** stone chip protector can be used on the following surfaces:-

- Suitably prepared bare metal. For overcoating aluminium, **ACID #8** etch primer is recommended.
- Original paint surfaces (with the exception of thermoplastic acrylics).

Thoroughly clean and degrease old paint surfaces with a suitable spirit wipe or thinner. Wet flat with 400 grade paper. For bare metal use 180 grade paper. Re-clean and dry.

### Health and Safety Statement

FOR PROFESSIONAL USE ONLY. Read full instructions before use.

**IMPORTANT:** This product contains hazardous materials and therefore appropriate personal protective equipment should always be used.

Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at [WWW.U-POL.COM](http://WWW.U-POL.COM). U-POL disclaim any liability where the user does not wear the recommended personal protective equipment.

### Application

Shake the tin before use. Apply with a clean Schutz gun or brush. Allow approximately 10-15 mins. for the solvent to flash off when building a thick coat.

### Thinners

**GRAVITEX PLUS** is supplied ready for use. However, up to 5% of good quality cellulose thinners may be added to vary the texture. Use cellulose thinners or similar proprietary products to clean the gun after use.

### Build and pressure

One coat of **GRAVITEX PLUS** will give a build of approximately 100-150 microns and a pressure of between 2.76 - 4.82 BAR is required at the gun. Less or more pressure will give a flatter or more rippled effect.

### Drying time

Approximately 2 hours at normal shop temperature or 30 mins. at low bake (80°C). Drying time is dependent on film thickness, humidity and temperature.

### Over-painting

**GRAVITEX PLUS** may be over-painted with most paint systems. With 2 pack acrylic paints its can be over-painted wet on wet. For optimum gloss and protection from fading, the use of a U.V Clear is recommended.

### Product codes

UP721 - Black Color/ 1L tin.  
UP722 - White Color/ 1L tin.  
UP723 - Gray Color/ 1L tin.

USA U-POL Representative - Sanders and Associates Inc. 1263 Route 31 South, Lebanon, NJ 08833

Tel: (908) 730 8858 or (800) 340 7824 Fax: (908) 730 6621 or (800) 787 5150

E-mail [upol@earthlink.net](mailto:upol@earthlink.net) Website : [WWW.U-POL.COM](http://WWW.U-POL.COM)